
Full Energy FEL-129



▼ Picture



Dimension



▼ Datasheet

| | Normal Volatage | | | | |
|---|----------------------|--|--------|--|--|
| | Rated | Capacity(C10) | 9Ah | | |
| Capacity 25°C(77°F) Internal Resistance | | 10 Hour rate(1.8V) | 9Ah | | |
| | | 3 Hour rate(1.8V) | 7.76Ah | | |
| | | 1 Hour rate(1.75V) | 5.85Ah | | |
| | | 25℃(Full Charged Battery) | ≦19mΩ | | |
| | | 40°C(104°F) | 102% | | |
| Discharge | Current | 25°C(77°F) | 102% | | |
| (10 hc | our) | 0°C(32°F) | 85% | | |
| | | -15°C(5°F) | 65% | | |
| | | 3 months later | 91% | | |
| Self Disc | | 6 months later | 82% | | |
| 25°C(7 | /°F) | 12 months later | 64% | | |
| Charge Method 25°C(77°F) | Floating Charge | Current:0.05C-0.15C Voltage:13.6V-13.8V | | | |
| | Equalizing Charge | Current:0.05C-0.15C Voltage:14.2V-14.5V | | | |

▼ Specification

| | Length | 151±2mm |
|-----------|--------------|-----------|
| Dimension | Width | 65±2mm |
| | Height | 94±2mm |
| | Total Height | 100±2mm |
| Termin | al | F1/F2 |
| Net Wei | ght | 2.40kg±3% |
| Gross We | eight | 2.45kg±3% |

▼ Certification















▼ Application、Advantages、Features

Application

- **■**Control System, Alarm system, Power system, Railway system
- Emergency Light, Emergency Lighting System, Backup power supply, UPS
- \blacksquare Telecom Equipment, Fire and Security Sytem, Power Station
- Electric Tools, Electric Toys

Advantages

- Design Life:10 years
- Safe and Reliable Seal
- \blacksquare High Specific energy, Low internal resistance, Low self-discharge rate
- Strong Charge acceptance and High sealing response efficiency

Features

- ☑ High-strength ABS plastic battery,Compact struture,Impact resistance and Seismic capacity
- Special Lead-based multi-element alloy grid, Low internal resistance, Strong charging acceptance ability
- ▶ New plate manufacturing process, High active material utilization rate
- High-purity electrolyte and special additives, Low self-discharge rate
- Multi-layer sealing technology and special sealant ensure that the battery has no leakage and no acid over, Safe and reliable




▼ Constant Current Discharge Characteristics (Amperes at 77°F25°C)

| Volt/ | Time | 5min | 10min | 15min | 30min | 1h | 2h | 3h | 4h | 5h | 10h | 20h |
|--------|------|------|-------|-------|-------|------|------|------|------|------|------|------|
| 9.60V | A | 26.7 | 16.9 | 13.2 | 7.46 | 4.59 | 2.51 | 1.74 | 1.44 | 1.22 | 0.66 | 0.36 |
| 9.00 V | W | 298 | 191 | 151 | 85.4 | 53.1 | 29.3 | 20.6 | 17.1 | 14.6 | 7.95 | 4.26 |
| 0.001/ | Α | 25.9 | 16.4 | 12.9 | 7.31 | 4.52 | 2.49 | 1.72 | 1.43 | 1.21 | 0.66 | 0.35 |
| 9.90V | W | 289 | 185 | 147 | 83.7 | 52.3 | 29.2 | 20.5 | 17.0 | 14.5 | 7.92 | 4.25 |
| 10.2V | Α | 24.9 | 15.8 | 12.4 | 7.08 | 4.40 | 2.47 | 1.71 | 1.42 | 1.21 | 0.66 | 0.35 |
| 10.2 V | W | 278 | 178 | 142 | 81.2 | 51.0 | 28.9 | 20.3 | 16.9 | 14.4 | 7.88 | 4.23 |
| 10.5V | Α | 23.8 | 15.1 | 12.0 | 6.91 | 4.31 | 2.43 | 1.70 | 1.41 | 1.20 | 0.65 | 0.35 |
| 10.5 V | W | 266 | 170 | 137 | 79.2 | 50.0 | 28.5 | 20.2 | 16.8 | 14.3 | 7.84 | 4.20 |
| 10.8V | Α | 22.5 | 14.2 | 11.4 | 6.66 | 4.18 | 2.37 | 1.65 | 1.36 | 1.16 | 0.64 | 0.34 |
| 10.0 V | W | 251 | 161 | 130 | 76.3 | 48.4 | 27.8 | 19.6 | 16.3 | 13.9 | 7.68 | 4.12 |


Above are cycle teats

▼ Discharge and Charge Characteristics


Charge Characteristics Curve




Temperature Effects on Capacity



Discharge Characteristics Curve



Cycle Life in Relation to Depth of Discharge



▼ Battery main material

| Name | Positive Plate | Negative Plate | Battery Case | Battery Cover | Vent Valve | Terminal | Seperator | Electrolyte |
|----------|------------------------|----------------|--------------|---------------|------------|-------------|------------|---------------|
| Material | High tin Alloy Lead | Alloy Lead | ABS | ABS | Rubber | Lead/Copper | Fiberglass | Sulfuric Acid |